







DIAMONT



	DIAMONT - Step 1 H 9000 BC 020 (15°C – 25°) BC 030 (>25°C) Mix well and strain before application.	100% by vol. 5% by vol.	depending on color 5 g
	 DIAMONT - Step 2 SPECIAL CRYSTAL BASE BC 020 (15°C – 25°C) BC 030 (>25°C) Mix well and strain before application.	60% by vol.	53 g
 Viscosity at 20°C: ISO 4 cup: DIN 4 cup:	22 to 28 seconds 14 to 16 seconds		
	Potlife:	Step 1: Step 2:	5 hours at 20°C 24 hours at 20°C
	HVLP gravity-feed spraygun Compliant gravity-feed spraygun	1.3 – 1.5 mm 1.3 – 1.4 mm	0.7 bar at the nozzle 2.0 bar
	Number of spraycoats: Film thickness:	Solid colors 2 15 – 20 µm	Metallic and pearl effect colors 2 + 1 to match effect 15 µm
	Съхнене при 20°C	15 мин.	

Завършване

След изчакване, нанесете R-M лак мокро-в-мокро.

Инструкции за безопасност

Възможно е този продукт да съдържа частици < 0.1 µm.

Само за професионална употреба.

Моля, спазвайте препоръките за безопасност и носете защитно облекло.