

Чисто черно SC 203

Област на приложение

Чисто черно за UNO HD CP.

Допълнителна информация

Техническа информация

Съдържание на солидни вещества 63 % ± 2	Плътност 0.970 – 1.070 g/cm ³
Температура на съхранение мин. 5°C до макс. 45°C	Срок на годност 36 месеца

Приложение

Разбъркайте добре преди употреба.

Използвайте SC 820 / R 2100 разребител за малки поправки или при ниски температури. Използвайте по-бавния SC 880 / R 2300 втвърдител при температури над 25°C или за големи детайли.

Почистване / Подготовка

Почистете с PK 2000.

Шлайфайте с P400 (фюлер или добре втвърдена стара конвенционална боя).

Почистете с PK 2000.

ИЛИ нанесете R-M фюлер мокро-в-мокро или уплътнител.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mppaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2015



