

Technical Information

PK 1000 / PK 2000



Soak a clean and dry lint-free cloth with PK 1000 or PK 2000.
Clean small areas of approx. 0.5 m² of the surface to be painted and wipe these areas immediately afterwards with a dry cloth of the same quality.
PK 1000 and PK 2000 should not dry on the surface being treated.

Attention:

Some 1K primers may suffer surface etching from the use of PK 1000. In this case, ensure a good flash-off so that no solvents will be trapped in the new paint system. In extreme cases, remove the 1K primer coat before applying the new paint system.

Finishing

Continue with the next step of the repair process.

Safety instructions

PK 1000: 2004/42/IIB(all)(200)186: The EU limit value for this product (product category: IIB.all) in ready-for-use form is max 200 grams of VOC per liter. The VOC content of this product is 186 g/l.

PK 2000: 2004/42/IIB(all)(200)198: The EU limit value for this product (product category: IIB.all) in ready-for-use form is max 200 grams of VOC per liter. The VOC content of this product is 198 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of these products please adhere to the actual safety recommendations and the personal protective equipment.